




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09J 189/00, A61L 25/00	A1	(11) International Publication Number: WO 99/52988 (43) International Publication Date: 21 October 1999 (21.10.99)
(21) International Application Number: PCT/GB99/01080 (22) International Filing Date: 8 April 1999 (08.04.99) (30) Priority Data: 9807777.9 9 April 1998 (09.04.98) GB (71) Applicants (for all designated States except US): MARS UK LIMITED [GB/GB]; 3D Dundee Road, Slough, Berkshire SL1 4LW (GB). BTTG [GB/GB]; Wira House, West Park Ring Road, Leeds LS16 6QL (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): NELSON, Gordon [GB/GB]; 7 Stonyford Road, Sale, Cheshire M33 2FJ (GB). JONES, Christopher, Andrew [GB/GB]; 5 Woodland Road, West Bridgford, Nottingham NG2 5AB (GB). (74) Agent: DAVIES, Jonathan, Mark; Reddie & Grose, 16 Theobalds Road, London WC1X 8PL (GB).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>

(54) Title: ADHESIVES**(57) Abstract**

The invention relates to water resistant adhesives. Many conventional adhesives are less effective or ineffective if the surfaces that are to be bonded together are wet or if water is applied to the bond after it has been formed. The invention provides a composition for use as an adhesive which comprises an extensin protein; and either a non-enzymatic bifunctional crosslinking agent; or a phenol oxidase and a phenol hydroxylase. Adhesives formed using compositions according to the invention have excellent strength, durability and water resistant properties.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

Adhesives

The present invention relates to water resistant adhesives.

5 Adhesives are widely used both domestically and industrially. They are typically applied to dry first and second surfaces to bond the surfaces together, for example as bonding agents to bond together particulate matter, or to adhere other solid materials such as woods and metals. It
10 is often desired to bond surfaces together when one or more of the surfaces is wet. Many adhesives are, however, less effective or ineffective if the surfaces that are to be bonded together are wet or if water is applied to the bond after it has been formed. Consequently, much effort has
15 been spent trying to identify and develop adhesives which are effective in wet environments.

Marine mussels are able to attach themselves to a variety of surfaces under water forming strong and durable bonds with those surfaces. The precise mechanism by which
20 mussels achieve this adhesion is not known. J.H.Waite has described the proposed involvement of catechol oxidase and a phenolic protein (Mussel Beards: a coming of age. Chemistry & Industry, 1991, 607-611). The mussel polyphenolic protein is a highly repetitive protein which
25 comprises 80 tandem repeats of a decapeptide of the sequence: Ala-Lys-Pro-Ser-Tyr-Pro-Pro-Thr-Tyr-Lys. The mussel protein is particularly rich in the amino acid 3,4-dihydroxyphenyl-L-alanine (L-dopa). Catechol oxidase occurs extensively throughout nature and is known to catalyse the
30 ortho hydroxylation of phenols and oxidation of the resulting catechols to o-quinones. Waite proposed, therefore, that catechol oxidase catalyses oxidation of the L-dopa residues in the mussel polyphenolic protein to L-quinone. It was suggested that adhesion results from a

- 2 -

combination of coupling of peptidyl-dopa to the bound surface and crosslinking of the polyphenolic protein by reaction of peptidyl-dopa-quinone with nucleophiles such as the e-amino group of lysine residues in the protein.

5 A catechol oxidase from mushrooms known as mushroom tyrosinase is available commercially and has been shown to hydroxylate tyrosine residues in synthetic decapeptides identical in sequence to the repeat sequences in the polyphenolic protein (Marumo K. and Waite J.H. (1986)
10 Optimization of hydroxylation of tyrosine and tyrosine-containing peptides by mushroom tyrosinase. *Biochemica et Biophysica Acta* **872**, 98-103).

 Large scale production of the mussel polyphenolic protein has been attempted with a view to production of a
15 commercial adhesive which can be crosslinked by mushroom tyrosinase. Methods for isolation of the polyphenolic protein from mussels are described in US 4 496 397, US 4 585 585, and US 4 687 740. None of these methods, however, have proved to be commercially viable because the
20 polyphenolic protein can only be isolated in small quantities.

 WO 97/19141 describes a method of manufacture of an adhesive comprising crosslinking first and second molecules such as gelatin and chitosan, each having one or more
25 aromatic groups, via at least one quinone group. Gelatin and chitosan are readily available and adhesives formed by this method show some resistance to water. However, the bonds formed are not as strong and durable as those formed by the mussel polyphenolic protein. A further disadvantage
30 is that gelatin is not soluble in water at room temperature and has to be heated before use. Chitosan is only soluble at low pH.

 It is desired therefore to produce bioadhesives which are effective in wet environments, which can be produced
35 cheaply in bulk quantities, and which have improved properties over known readily produced bioadhesives.

- 3 -

Extensin proteins are hydroxyproline-rich glycoproteins present in the cell walls of dicotyledonous plants. The exact function of extensins is not known, but they have been proposed to play a role in the structure of plant cell walls. Extensins also accumulate in plant cell walls upon wounding and pathogenic attack and are therefore also thought to be involved in defence. It is known that extensins are inherently sticky and their adhesion to glass, polypropylene, and polycarbonate has been described in a paper by Miller, J.G. and Fry, S.C., (1993) (Spinach extensin exhibits characteristics of an adhesive polymer. *Acta Bot. Neerl.* **42**(2), 221-231). However, the mechanism of adhesion here appears to be a mixture of purely intramolecular forces such as hydrogen bonding and ionic interactions. Oxidative processes are not involved as the adhesion is not inhibited using reducing agents such as ascorbate, mercaptoethanol and dithiothreitol. Although native non-crosslinked proteins can adhere to inert substances, the set adhesive will be sensitive to moisture. Ultimately strength loss and bond breakage will become apparent. A successful commercial adhesive system must be crosslinked both to improve the strength of the adhesive and to ensure adhesion in wet environments and areas of high moisture.

Extensins have been proposed to form crosslinks by Fry, C.F., (1982) (Isodityrosine, a new crosslinking amino acid from plant cell wall glycoprotein. *Biochem.J.* **204**, 449-455). Fry suggested that hydrogen peroxide and a peroxidase enzyme such as horseradish peroxidase could be used to form isodityrosine bonds via an ether linkage between two tyrosine residues. Formation of dityrosine crosslinks via a biphenyl linkage between two tyrosines was not thought to occur. The formation of an isodityrosine bond and comparison of that linkage with the dityrosine linkage is represented in figure 1 of the accompanying drawings.

The proposed existence of such crosslinking suggests that extensins may form adhesives in the presence of

- 4 -

hydrogen peroxide and a peroxidase enzyme. However, it is most unlikely that formation of an adhesive based on addition of a cofactor such as hydrogen peroxide will be practical. Hydrogen peroxide is a relatively low viscosity liquid and would be very difficult to mix with other components of the adhesive which also tend to be relatively viscous. Hydrogen peroxide is also fairly reactive and it is likely that bond formation would occur too quickly after it is added to the other components of the adhesive. A further disadvantage of hydrogen peroxide is that it has a relatively short shelf-life. Any contamination from, for example, dirt would introduce bacteria, many of which contain catalase enzymes which breakdown hydrogen peroxide.

Peroxidase has also been proposed to be involved in the hydroxylation of L-tyrosine residues to L-Dopa (Klibanov A.M., Berman Z., and Alberti B.N. (1981) Preparative hydroxylation of aromatic compounds catalysed by peroxidase. *J. Am. Chem. Soc.* **103**, 6263-6264), suggesting an alternative role for peroxidase in crosslink formation similar to crosslink formation in the mussel polyphenolic protein adhesive. However, this reaction requires oxygen and dihydroxyfumaric acid and must be carried out at 0°C, otherwise non specific oxidation of other amino acids occurs. Use of peroxidase for crosslinking of extensin proteins has therefore not been thought to provide a viable way of producing a commercial adhesive.

It has surprisingly been found that extensin proteins have remarkable adhesive properties.

According to a first aspect of the invention there is provided a composition for use as an adhesive comprising:
an extensin protein; and either
a non-enzymatic bifunctional crosslinking agent; or
a phenol oxidase and a phenol hydroxylase.

According to a second aspect of the invention there is provided a composition for use as an adhesive comprising:
an extensin protein;
a phenol oxidase and a phenol hydroxylase; and

- 5 -

a non-enzymatic bifunctional crosslinking agent.

According to the invention there is also provided a method for forming an adhesive according to the first aspect of the invention which comprises admixing an extensin protein with either:

an amount of a non-enzymatic bifunctional crosslinking agent; or

an amount of a phenol oxidase and a phenol hydroxylase effective for inducing crosslinking of the protein.

Also according to the invention there is provided a method for forming an adhesive according to the second aspect of the invention which comprises admixing an extensin protein with an amount of a non-enzymatic bifunctional crosslinking agent, a phenol oxidase and a phenol hydroxylase effective for inducing crosslinking of the protein.

Each component of compositions according to the invention may be soluble in water.

When using a phenol oxidase and a phenol hydroxylase for crosslinking, it is possible to include as a cofactor a phenolic moiety which comprises at least one of a monohydroxy phenol group or a dihydroxy phenol group. Examples of phenolic moieties which comprise a dihydroxy phenol group include catechol and catechin. The cofactor should be soluble in water. The cofactor may be present at about 1% weight by volume of the composition.

The term "extensin protein" used herein is defined for the purposes of this application as covering:

(i) natural extensin proteins, such as plant extensins (for example carrot, spinach, etc.);

(ii) non-natural synthetic extensins, such as extensins produced chemically or by expression of recombinant DNA in a suitable host;

(iii) extensin derivatives (whether chemical or synthetic) which have amino acid sequences which differ from the extensin sequences by virtue of amino acid substitution, deletion, or addition, protease truncation or post

- 6 -

translational modification; but which retain extensin activity.

Natural extensin protein as referred to in (i) above is a plant protein rich in hydroxyproline, tyrosine and lysine residues. The content of hydroxyproline in carrot extensin is at least 50%, the content of tyrosine is at least 10.1%, and the content of lysine is at least 6.9%.

DNA encoding carrot extensin has been cloned (Chen J. and Varner J.E. (1985) An extracellular matrix protein in plants: characterisation of a genomic clone for carrot extensin. *EMBO J.* **4**, 2145-2151; Chen J. and Varner JE (1985) Isolation and characterisation of cDNA clones for carrot extensin and a proline-rich 33KDa protein. *Proc.Natl.Acad.Sci.USA* **82**, 4399-4403).

Derivatives of the extensin as referred to in (iii) above may be obtained by expression of a modified DNA including a modified extensin gene. A derivative of the extensin may be substantially free of carbohydrate.

The extensin protein may be present in the composition in an amount upto about 50% weight by volume of the composition, for example, the extensin protein may be present in the composition in an amount from about 20% to about 30% weight by volume of the composition.

A procedure for isolation of an extensin according to the invention from carrots is described below:

Carrot extensin proteins were isolated from cores (7mm) of phloem parenchyma sliced with a scalpel into 1mm thick slices. Carrot preparations (90g) (finely chopped or gently homogenised) were washed twice in distilled water and incubated in potassium phosphate buffer (5mM, pH 6.0) containing chloramphenicol (50mg/ml) for three days at 28°C with shaking. The extraction buffer was exchanged each day. On completion, the carrots were washed in distilled water and immersed in a solution (600ml) containing polyvinyl polypyrrolidone (PVPP) (9g) and dithiothreitol (DTT) (5mM, final concentration). The tissue was homogenised for two minutes in a blender, pelleted by centrifugation and washed

- 7 -

with eight litres of distilled water. The cell wall pellet was further extracted (3 times) with 200ml of a solution containing calcium chloride (0.2M final concentration), DTT (5mM final concentration) and PVPP (9g). On centrifugation the supernatants were pooled, filtered to remove any solid material and reduced to a volume of 50ml using ultrafiltration (10,000 molecular weight cut-off). The concentrated extract was dialysed overnight in distilled water at 4°C and further reduced in volume to 10ml by ultrafiltration. Each 10ml volume was adjusted with 1M tris/HCl (pH 8) to give a final tris concentration of 10mM. The material was then applied to a cation exchange column (12 x 1.5 cm) (CM-Sepharose CL-6B) previously equilibrated with tris/HCl (10mM, pH 8) and the protein fractions eluted using one column volume of tris/HCl (pH 8) followed by a linear gradient (60ml) of 10-300mM tris/HCl (pH 8). The elution profile was monitored at 280nm and the fractions (3ml) corresponding to each peak were pooled and dialysed overnight with sodium acetate (100mM, pH 6) at 4°C. The dialysed samples were freeze-dried and weighed before further analysis. In all purifications peak 1 from the cation exchange column was ignored as it was primarily made up of PVPP.

It is noted herein that peroxidases are not phenol oxidases. Peroxidases act by hydrolysing hydrogen peroxide. It is possible that oxygen liberated by this reaction can oxidise phenolics, but this oxidation does not occur by an enzymatic process. Phenol oxidation is not possible in the presence of a peroxidase without the addition of hydrogen peroxide. It is also noted herein that peroxidases are not phenol hydroxylases.

The phenol oxidase and the phenol hydroxylase may be a tyrosinase. The composition can contain at least 0.005% weight by volume of tyrosinase. Tyrosinase has the advantage that it is readily available from a variety of sources. The tyrosinase may be a mushroom tyrosinase. The mushroom tyrosinase may be *Agaricus bisporus* tyrosinase.

- 8 -

The non-enzymatic bifunctional crosslinking agent may be present in the composition from about 0.1% to about 5% weight by volume of the composition. The non-enzymatic bifunctional crosslinking agent may be any non-enzymatic bifunctional crosslinking agent capable of inducing crosslinking of a composition for use as an adhesive according to the invention. The non-enzymatic bifunctional crosslinking agent may be at least one of glutaraldehyde, a di-isocyanate, or a quinone. The di-isocyanate may be Trixene, for example Trixene BI 7986 (Baxenden). Trixene has the advantage that it is blocked and unreactive until the temperature reaches 130°C. Compositions according to the invention that comprise Trixene may therefore form a thermo-setting adhesive. The quinone may be a benzoquinone or a derivative thereof. The amount of the benzoquinone in the composition can be about 1% weight by volume of the composition. The benzoquinone may be 1,2-benzoquinone, 1,3-benzoquinone, or 1,4-benzoquinone.

It has been found that the rate of oxidation of groups may be conveniently controlled by varying the amount of phenol oxidase and phenol hydroxylase that is added, allowing the rate of linkage to be readily controlled. The rate of linkage may also be controlled by varying the amount of the non-enzymatic bifunctional crosslinking agent.

When compositions according to the invention that contain the non-enzymatic bifunctional crosslinking agent form crosslinks, the non-enzymatic bifunctional crosslinking agent reacts with the ε-amino group of lysine residues in the extensin protein. Each molecule of non-enzymatic bifunctional crosslinking agent can react with upto two lysine residues. When the two lysine residues are in different protein molecules, crosslinks are formed between different protein molecules. When the two lysine residues are in the same protein molecule, crosslinks are formed within the same protein molecule.

When compositions according to the invention that comprise the phenol oxidase and the phenol hydroxylase form crosslinks, the phenol hydroxylase catalyses the

- 9 -

hydroxylation of the phenol group of tyrosine residues in the protein to form a dihydroxy phenol group and the phenol oxidase catalyses the oxidation of the dihydroxy phenol group to form a quinone group. The quinone group of the modified tyrosine residue may then react with the ϵ -amino group of two lysine residues in the protein. When one or both of the lysine residues are in the same protein molecule as the modified tyrosine residue containing the quinone group, intramolecular crosslinking occurs. When one or both of the lysine residues are in different protein molecules to the modified tyrosine residue containing the quinone group, intermolecular crosslinking occurs.

Tyrosinase has the advantage that it is a phenol hydroxylase and a phenol oxidase. It will be appreciated therefore that compositions according to the invention which comprise tyrosinase have the advantage that a separate phenol oxidase and a phenol hydroxylase do not have to be added to the composition because the phenol oxidase and the phenol hydroxylase activity are on a single molecule.

In the accompanying drawings:

Figure 1 shows the formation of an isodityrosine bond and comparison of that linkage with the dityrosine linkage;

Figure 2 shows the hydroxylation and oxidation of a tyrosine residue by tyrosinase and reaction of the oxidised tyrosine residue with the ϵ -amino group of a lysine residue in the same protein molecule.

When compositions according to the invention that comprise the phenol oxidase and the phenol hydroxylase further include a cofactor which comprises a phenolic moiety with a monohydroxy phenol group, the phenol hydroxylase catalyses the hydroxylation of the monohydroxy phenol group in the cofactor to form a dihydroxy phenol group and the phenol oxidase catalyses the oxidation of the dihydroxy phenol group to form a quinone group. The quinone group of the modified cofactor may then react with the ϵ -amino group of lysine residues in the protein to form crosslinks within the same protein molecule or between different protein molecules.

- 10 -

When compositions according to the invention that comprise the phenol oxidase and the phenol hydroxylase further include a cofactor which comprises a phenolic moiety with a dihydroxy phenol group, the phenol oxidase catalyses the oxidation of the dihydroxy phenol group of the cofactor to form a quinone group. The quinone group of the modified cofactor may then react with the ϵ -amino group of lysine residues in the protein to form crosslinks within the same protein molecule or between different protein molecules. Thus, a cofactor comprising a monohydroxy phenol group or a dihydroxy phenol group may be used to increase the number of crosslinks formed compared to compositions according to the invention which comprise the phenol oxidase and the phenol hydroxylase that do not include the cofactor. The number of crosslinks which can potentially be formed may also be increased by increasing the number of tyrosine and/or lysine residues in the extensin protein by recombinant means. However, care should be taken not to increase the number of crosslinks formed too much as over-crosslinked adhesives can be brittle.

It will be appreciated that compositions according to the invention that comprise a cofactor which includes a dihydroxy phenol group may form crosslinks in the absence of the phenol hydroxylase. Consequently, there is also provided according to the invention a composition for use as an adhesive which comprises:

- an extensin protein;
- a cofactor comprising a dihydroxy phenol group;
- a phenol oxidase; and optionally
- a non-enzymatic bifunctional crosslinking agent.

There is also provided a method for forming an adhesive which comprises admixing an extensin protein with an amount of a cofactor comprising a dihydroxy phenol group, a phenol oxidase, and optionally a non-enzymatic bifunctional crosslinking agent effective for inducing crosslinking of the protein.

According to the invention there is also provided a kit for manufacture of an adhesive, the kit comprising separate

- 11 -

components, wherein admixture of the separate components forms a composition according to the invention.

According to the invention there is also provided a kit for manufacture of an adhesive that comprises separate first and second components, the first component comprising an
5 extensin protein, the second component comprising: either a non-enzymatic bifunctional crosslinking agent; or a phenol oxidase and a phenol hydroxylase and optionally a cofactor;

10 wherein admixture of the first and second components forms a composition according to the invention.

Also according to the invention there is provided a kit for manufacture of an adhesive that comprises separate first and second components, the first component comprising an
15 extensin protein, the second component comprising a non-enzymatic bifunctional crosslinking agent and a phenol oxidase and a phenol hydroxylase and optionally a cofactor, wherein admixture of the first and second components forms a composition according to the invention.

20 Adhesives formed using compositions according to the invention have excellent strength, durability and water resistant properties. They are readily produced in bulk quantities and at low cost. The strength of adhesives according to the invention has been found to be at least as
25 good as the strength of conventional water resistant adhesives.

Adhesives according to the invention have been found to have several uses. Adhesives according to the invention may adhere to water-absorbent substrates and can be used to
30 adhere such substrates together. Adhesives of the present invention may adhere to a substrate having a hydroxy aromatic, dihydroxy aromatic, hydroxy phenone or amino group and can be used to adhere such substrates together. For example the substrate may be wood, leather, cotton, paper,
35 carpet, or a textile.

Adhesives according to the invention have also been found to adhere to non water-absorbent substrates and can be used to adhere non water-absorbent substrates to each other

- 12 -

or to water absorbent substrates. For example, the non water-absorbent substrate may be a metal or a plastic.

Adhesives according to the invention may be used to bind together particulates. Examples of particulates
5 include sand and glass fibre.

Adhesives according to the invention may be used as an undercoat to a protective coating such as a paint or to a coating such as a non water-resistant adhesive. Undercoats comprising adhesives according to the invention have been
10 found to have the advantage that the coating that is subsequently applied to the undercoat is significantly more resistant to the effects of water than coatings applied in the absence of the undercoat or to coatings applied to a conventional undercoat.

Adhesives according to the invention may be used as a
15 suture to close wounds. Sutures formed according to the invention have the advantage that they are resistant to water and may have reduced antigenicity compared to conventional sutures.

Adhesives according to the invention may be used as a
20 gelling agent in food products.

According to the invention there is also provided a pharmaceutical composition comprising a pharmaceutically active ingredient and a crosslinked adhesive composition
25 according to the invention.

- 13 -

Figure Legends

Figure 1 shows the formation of an isodityrosine crosslink (in compound (2)) by hydrogen peroxide and peroxidase from two tyrosines (1). Formation of a dityrosine crosslink (in
5 compound (3)) is not thought to occur.

Figure 2 shows a tyrosine residue (2) being hydroxylated (3) and subsequently oxidised (4) by tyrosinase, followed by reaction of the oxidised tyrosine residue (4) with the ϵ -amino group of a lysine residue (1) in the same protein
10 molecule to form an intramolecular crosslink (5).

Claims

1. A composition for use as an adhesive comprising:
an extensin protein; and either
a non-enzymatic bifunctional crosslinking agent; or
5 a phenol oxidase and a phenol hydroxylase.
2. A composition for use as an adhesive comprising:
an extensin protein;
a non-enzymatic bifunctional crosslinking agent; and
a phenol oxidase and a phenol hydroxylase.
- 10 3. A composition according to claim 1 or 2 which further
comprises a cofactor when the composition comprises a phenol
oxidase and a phenol hydroxylase.
4. A method for forming an adhesive which comprises
admixing an extensin protein with either:
15 an amount of a non-enzymatic bifunctional crosslinking
agent; or
an amount of a phenol oxidase and a phenol hydroxylase
effective for inducing crosslinking of the protein.
5. A method for forming an adhesive which comprises
20 admixing an extensin protein with an amount of a non-
enzymatic bifunctional crosslinking agent, a phenol oxidase
and a phenol hydroxylase effective for inducing crosslinking
of the protein.
6. A method for forming an adhesive which comprises
25 admixing an extensin protein either with an amount of a
cofactor, a phenol oxidase and a phenol hydroxylase
effective for inducing crosslinking of the protein or with
an amount of a cofactor, a non-enzymatic bifunctional
crosslinking agent, a phenol oxidase and a phenol
30 hydroxylase effective for inducing crosslinking of the
protein.

- 15 -

7. A composition or method according to claim 3 or 6 in which the cofactor comprises a phenolic moiety which comprises at least one of a monohydroxy phenol group or a dihydroxy phenol group.
- 5 8. A composition or method according to claim 3, 6, or 7 in which the cofactor is soluble in water.
9. A composition or method according to claim 7 or 8 in which the cofactor comprises catechin.
- 10 10. A composition or method according to any of claims 7 to 9 in which the cofactor comprises catechol.
11. A composition or method according to any preceding claim in which the non-enzymatic bifunctional crosslinking agent comprises glutaraldehyde.
- 15 12. A composition or method according to any preceding claim in which the non-enzymatic bifunctional crosslinking agent comprises a di-isocyanate.
13. A composition or method according to claim 12 in which the di-isocyanate is Trixene.
- 20 14. A composition or method according to any preceding claim in which the non-enzymatic bifunctional crosslinking agent comprises a quinone.
15. A composition or method according to claim 14 in which the quinone is a benzoquinone.
- 25 16. A composition or method according to any preceding claim in which the phenol oxidase and the phenol hydroxylase is a tyrosinase.

- 16 -

17. A composition or method according to claim 16 in which the tyrosinase is a mushroom tyrosinase.

18. A composition or method according to claim 17 in which the mushroom tyrosinase is *Agaricus bisporus* tyrosinase.

5 19. A composition for use as an adhesive which comprises:
an extensin protein;
a cofactor comprising a dihydroxy phenol group;
a phenol oxidase; and optionally
a non-enzymatic bifunctional crosslinking agent.

10 20. A method for forming an adhesive which comprises
admixing an extensin protein with an amount of a cofactor
comprising a dihydroxy phenol group, a phenol oxidase, and
optionally a non-enzymatic bifunctional crosslinking agent
effective for inducing crosslinking of the protein.

15 21. Use of a composition or method according to any
preceding claim for binding substrates together.

22. Use according to claim 21 in which the substrates are
non water-absorbent.

20 23. Use according to claim 21 in which the substrates are
water absorbent.

24. Use according to claim 21 in which the substrates
comprise a non water-absorbent substrate and a water
absorbent substrate.

25 25. Use according to claim 22 or 24 in which the non water-
absorbent substrate or substrates comprise at least one of
metal or plastic.

- 17 -

26. Use according to claim 23 or 24 in which the water absorbent substrate or substrates comprise at least one of wood, leather, cotton, paper, carpet, or textile.
27. Use according to claim 21 as a binder of particulates.
- 5 28. Use according to claim 27 in which the particulates comprise at least one of sand or glass fibre.
29. Use according to claim 21 as an undercoat to a coating.
30. Use according to claim 29 in which the coating is a paint.
- 10 31. Use according to claim 29 in which the coating is an adhesive.
32. Use according to claim 21 as a suture for closing a wound.
33. Use according to claim 32 in a method for closing a
15 wound.
34. Use according to claim 21 as a gelling agent in food products.
35. A pharmaceutical composition comprising a
pharmaceutically active ingredient and a crosslinked
20 adhesive composition according to any of claims 1 to 3 or 7 to 19.
36. A kit for manufacture of an adhesive, the kit comprising separate components, wherein admixture of the separate components forms an adhesive composition according
25 to any of claims 1 to 3 or 7 to 19.
37. A kit for manufacture of an adhesive that comprises separate first and second components, the first component

- 18 -

comprising an extensin protein, the second component comprising: either

a non-enzymatic bifunctional crosslinking agent; or
a phenol oxidase and a phenol hydroxylase and optionally a
5 cofactor;

wherein admixture of the first and second components forms a composition according to any of claims 1 to 3 or 7 to 18.

38. A kit for manufacture of an adhesive that comprises separate first and second components, the first component
10 comprising an extensin protein, the second component comprising a non-enzymatic bifunctional crosslinking agent and a phenol oxidase and a phenol hydroxylase and optionally a cofactor, wherein admixture of the first and second components forms a composition according to any of claims 2,
15 3 or 7 to 18.

39. A composition for use as an adhesive substantially as described with reference to figure 2 of the accompanying drawings.

40. A method for forming an adhesive substantially as
20 described with reference to figure 2 of the accompanying drawings.

41. A kit for manufacture of an adhesive substantially as described with reference to figure 2 of the accompanying drawings.

FIGURE 1





FIGURE 2



INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/01080

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09J189/00 A61L25/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09J A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	PATENT ABSTRACTS OF JAPAN vol. 18, no. 316 (C-1213), 16 June 1994 (1994-06-16) & JP 06 070972 A (NIPPON B X I KK), 15 March 1994 (1994-03-15) abstract & DATABASE WPI Week 9415 Derwent Publications Ltd., London, GB; AN 123366 --- -/--	1-41

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 July 1999

Date of mailing of the international search report

29/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lensen, H

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/01080

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	HIROYUKI YAMAMOTO ET AL.: "Cross-linking and gel-formation of water-soluble lysine polypeptides." INTERNATION JOURNAL OF BIOLOGICAL MACROMOLECULES, vol. 14, no. 2, 1 April 1992 (1992-04-01), pages 66-72, XP002108796 London page 71	1-41
Y	WO 96 20284 A (INDENA S.P.A.) 4 July 1996 (1996-07-04) page 3, line 18 - page 4, line 15	1-41
A	US 5 202 256 A (KATHY J. MAUGH ET AL.) 13 April 1993 (1993-04-13)	
A	EP 0 244 688 A (BIO-POLYMERS INC.) 11 November 1987 (1987-11-11)	
A	PATENT ABSTRACTS OF JAPAN vol. 17, no. 180 (C-1046), 8 April 1993 (1993-04-08) & JP 04 334396 A (HITACHI CHEM CO LTD), 20 November 1992 (1992-11-20) abstract & DATABASE WPI Week 9301 Derwent Publications Ltd., London, GB; AN 5540	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/01080

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 06070972 A	15-03-1994	JP 2688559 B	10-12-1997
WO 9620284 A	04-07-1996	IT MI942663 A	28-06-1996
		AU 692654 B	11-06-1998
		AU 4346896 A	19-07-1996
		CA 2208960 A	04-07-1996
		CN 1171822 A	28-01-1998
		CZ 9702024 A	12-11-1997
		EP 0800585 A	15-10-1997
		FI 972757 A	18-08-1997
		HU 77703 A	28-07-1998
		JP 10510432 T	13-10-1998
		NO 972984 A	26-06-1997
		PL 321004 A	24-11-1997
		SI 9520146 A	28-02-1998
		SK 86097 A	10-12-1997
US 5202256 A	13-04-1993	US 5049504 A	17-09-1991
		AU 1180488 A	16-06-1988
		DK 414688 A	22-07-1988
		EP 0332660 A	20-09-1989
		WO 8803953 A	02-06-1988
		US 5202236 A	13-04-1991
		CA 1282020 A	26-03-1991
		JP 61085400 A	30-04-1986
		US 5242808 A	07-09-1993
		US 5149657 A	22-09-1992
EP 244688 A	11-11-1987	AT 68813 T	15-11-1991
		AU 2497288 A	23-03-1989
		AU 7188687 A	29-10-1987
		CA 1307081 A	08-09-1992
		DE 3773986 A	28-11-1991
		DK 205187 A	26-10-1987
		FI 871727 A	26-10-1987
		GR 3003622 T	16-03-1993
		JP 63023670 A	30-01-1988
		US 5015677 A	14-05-1991
JP 04334396 A	20-11-1992	NONE	